

# 102 Asphalt Primer

**DESCRIPTION:**

Karnak #102 Asphalt Primer is a material composed of selected asphalts and refined solvents. It has good resistance to temperature change, yet dries to a tough film. Karnak #102 Asphalt Primer provides a firm base and better adhesion for the application of asphalt coatings. The Karnak #102 Asphalt Primer is **not** to be used as a roof coating.

**USES:**

Karnak #102 Asphalt Primer's uses include prime coat over brick, metal surfaces, gypsum, concrete block and cinder block. It is also used to coat interior faces of masonry walls above grade and for all back- up materials such as stone, brick and concrete.

**APPLICATION:**

Karnak #102 Asphalt Primer is easily applied by brush, roller or spray equipment.

**BRUSH APPLICATION:**

Apply with a wide, fiber brush at a rate of .5 to 1 gallon per 100 sq. ft. Work primer into all cracks, holes and crevices.

**SPRAY APPLICATION:**

Utilize a standard heavy duty spray pump using heavy duty guns and nozzles. Equipment manufacturer should be consulted for more complete information. Apply at the rate of .5 to 1 gallon per 100 sq. ft.

**NOTE:**

Primer must be thoroughly dry prior to coating applications.

**COVERAGE RATE:**

Apply at the rate of .5 to 1 gallon per 100 square feet depending upon the condition and porosity of the surface to be primed.

**PHYSICAL PROPERTIES**

Weight per gallon:	7.80
Solids by Weight:	70%
Solids by Volume:	64%
Color:	Black
Dry Time:	8 to 24 hrs.
Service Temperature Range:	-40°F to 180°F

**KARNAK**

330 CENTRAL AVENUE, CLARK, NJ 07066  
732-388-0300 • 800-526-4236 • FAX: 732-388-9422  
WEB: <http://www.karnakcorp.com>

## 102 Asphalt Primer

**CAUTION:**

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not** induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin.** Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

**CARE OF TOOLS:**

Tools and other equipment should be thoroughly cleaned with mineral spirits, taking necessary precautions when handling combustible materials.

**PACKAGING:**

Available in 5 gallon pails and 55 gallon drums.

**If further information is needed, contact Karnak Technical Services at 1-800-526-4236.**

Please see page 222 for additional mold and safety information

**KARNAK**

330 CENTRAL AVENUE, CLARK, NJ 07066  
732-388-0300 • 800-526-4236 • FAX: 732-388-9422  
WEB: <http://www.karnakcorp.com>