197 Karnastatic "Slaters" Cement

DESCRIPTION:

Karnak #197 Karnastatic Cement is prepared from a blend of selected asphalts, special additives, mineral fibers and refined solvents. This composition is then passed through a high speed mixer which results in a smooth trowel-like-consistency in the finished product.

Karnak #197 Karnastatic Cement dries to a firm and hard finish. Because of its rapid curing action, Karnak #197 Karnastatic Cement is dry to the touch in just a few hours.

USES:

Because Karnak #197 Karnastatic Cement will not run or sag on vertical surfaces, it is ideal for use on:

- Flashings and parapet walls.
- As a gutter liner for either metal or wooden gutters.
- Dampproofing exterior masonry walls.

SURFACE PREPARATION:

All surfaces should be clean and free of all dust, dirt, oil, grease, rust, loose paint, or other foreign matter.

COVERAGE RATE:

Apply by trowel to an average thickness of 1/8" (8 gallons per 100 sq.ft.).

SPECIFICATION:

ASTM D-4586 Type II Class I

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.



197 Karnastatic "Slaters" Cement

CARE OF TOOLS:

Tools and other equipment should be thoroughly cleaned with mineral spirits or Karna-Klean, taking necessary precautions when handling flammable materials.

PACKAGING:

Available in 5 gallon pails. If further information is needed, contact Karnak Technical Services at 1-800-526-4236.

Please see page 222 for additional mold and safety information.



p://www.karnakcorp.com FM1015