

## 230-2% Neo-Asphalt (trowel grade)

**DESCRIPTION:**

Karnak #230-2% Neo-Asphalt is a cold applied, rubberized asphalt cement, designed especially for use as an adhesive for paving blocks and pressed asphalt bricks. Eliminates the need for a hot kettle.

**SURFACE PREPARATION:**

All surfaces should be clean, free from oil, grease or other foreign matter.

**APPLICATION:**

Karnak #230-2% Neo-Asphalt can be applied to either concrete or macadam (blacktop) using a 1/16" serrated trowel. For best results, Karnak #230 2% Neo-Asphalt should be allowed to have a minimum of 2-3 hours open air time or until material becomes tacky and just skins over, prior to embedding the asphalt bricks.

**COVERAGE:**

Apply at the rate of 1.5 - 2 gallons per 100 sq. ft. Do not exceed coverage rate.

**PHYSICAL PROPERTIES:**

Viscosity @ 25C:	30,000-40,000 C.P.S.
Specific Gravity @ 25C:	1.02
Weight per Gallon @ 25C:	8.5 lbs.
% Solids by Weight:	68%
Softening Point of Rubber Blend:	150F
% Inorganic Material:	18%
% Long Fiber	10%
% Neoprene	2% min.

**CAUTION:**

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not** induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin.** Dispose of in an environmentally safe manner.

**CARE OF TOOLS:**

Tools and other equipment should be thoroughly cleaned with mineral spirits, taking necessary precautions when handling combustible materials.

**PACKAGING:**

Available in 5 gallon pails and 55 gallon drums.

**If further information is needed, contact Karnak Technical Services at 1-800-526-4236.**

Please see page 222 for additional mold and safety information.

**KARNAK**

330 CENTRAL AVENUE, CLARK, NJ 07066  
732-388-0300 • 800-526-4236 • FAX: 732-388-9422  
WEB: <http://www.karnakcorp.com>